

# MESSMER'S

## NATURAL WOOD FINISHES



## MOSO® Bamboo Finish NATURAL

Messmer's MOSO® Bamboo Finish is an oil based penetrating natural finish specifically designed for use on MOSO® Bamboo Outdoor products. MOSO® Bamboo Finish protects and conditions MOSO® Bamboo Outdoor products while maintaining a completely natural appearance.

### SPECIFICATIONS

#### VEHICLE TYPE

Solvent and VOC exempt solvent borne blend of oils and alkyds

#### COLORS

Available in Natural, a lightly pigmented transparent finish

#### VISCOSITY

15-18 seconds Zahn #2 at 77F

#### VOC CONTENT

Standard MOSO Finish <250 g/L (as supplied)

Low VOC MOSO Finish <100 g/L (as supplied)

#### SOLIDS BY VOLUME

250 VOC / 100 VOC Approx 49%

#### SOLIDS BY WEIGHT

250 VOC / 100 VOC Approx 48%

#### WEIGHT PER GALLON

7.5 to 8.5 lbs

#### COVERAGE

Rough Surface: 150 to 250 square feet per gallon

Smooth Surface: 200 to 300 square feet per gallon

#### DRY TIME

Allow 24 hours in good drying conditions

#### APPLY WITH

Brush, applicator pad, garden sprayer, airless sprayer

#### THINNING RECOMMENDATIONS

Thinning is not recommended.

#### CLEANUP

Use paint thinner. Dispose of waste in accordance with local, state and federal regulations.

#### PACKAGING

One gallon containers

#### SURFACE PREPARATION

Always clean a new bamboo deck after 12 weeks and a gray or dirty bamboo (or wood) deck before applying MOSO® Bamboo Finish. Use Messmer's WD Wood & Deck Cleaner (A) and Brightener (B) available in powder concentrates. Allow surface to completely dry for at least 24 to 48 hours. Previously stained or treated surface should be sufficiently weathered and cleaned to allow for complete penetration.

#### SPECIAL INSTRUCTIONS

Before applying, this product should be mixed thoroughly. Ensure that all settled material on bottom of can is evenly incorporated, and intermix all containers (box them).

Apply MOSO® Bamboo Finish when surface temperatures are between 45F and 90F. If surface is hot to the touch, it is too hot to apply product. Do not apply product if precipitation is expected within 24-48 hours.

Spray Application: Spraying is not recommended for decks. On vertical applications, back brush or roll to prevent over application, sags and runs. Cover surrounding areas to protect from overspray. For airless spray, use .015" to .019" tip size for best results.

Brush Application: To minimize lapping, maintain a wet edge lengthwise and do not break in the middle of boards.

**One coat is sufficient for most applications. Product not absorbed into the surface within 10 minutes must be removed to prevent a sticky / tacky deck and excess sheen.**

#### MORE INFO

Visit [messmers.com/moso](http://messmers.com/moso)

**\*\* DANGER \*\* - Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after each use, place rags, steel wool or waste in a sealed, water filled metal container.**